

## Greenblock Screen

**Colors:**

Dark Green

Properties		
Material Composition	100% Virgin Polypropylene with UV Additives	
Construction (tapes/inch)	Warp: 20	Weft: 10
Tenacity (lb/in) ASTM D-1662	Warp: > 60	Weft: > 90
Weight (oz/yd <sup>2</sup> ) ASTM D-1910	3.0 (+ 0.15 oz)	
Shade / Wind Blockage	95%	
U.V. Resistance (70% Tenacity Retained After 200 Hours) ASTM G-154-98	Warp: 85	Weft: 85
Water Permeability	4.2 gallons/yd <sup>2</sup> /second	

**Disclaimer:** Collins Company assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Collins Company disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.